

# EASIPOINT

## SLABFIX



### Preparation

Mark out areas where slabs are to be laid. Ensure that the surface is free from oil, grease, loose material and standing water to produce a sound, clean, dry surface.

### Mixing

Pour resin into polythene or rubber bucket. Add catalysed filler slowly whilst continuously mixing. Continue mixing until a uniform consistency is obtained

### Application

As the chemical reaction of setting is rapid, material should be placed as soon as mixing is complete.

Apply mixed mortar to the prepared substrate using a suitable trowel. Up to 25mm thickness of mortar may be placed in a single layer. Thicker beds should be placed in 25mm applications. Mortar should be well compacted onto prepared surface.

Place slab onto mortar bed and press down into the required position.

The material may be placed at temperatures between 0°C and 35°C.

### Yield

Each 14kg box will yield approximately 7 litres of mixed material.

**For further information and sales please contact:**

**EasiPoint Marketing Ltd**  
**Restoration House**  
**Drumhead Road**  
**Chorley North Industrial Estate**  
**Chorley, Lancs**  
**PR6 7DE**

**Tel: 01257 224900**  
**Fax: 01257 224901**

EasiPoint products are guaranteed against defective materials and manufacture. Products are sold subject to the EasiPoint Marketing Limited Terms and Conditions of Sale, copies of which are forwarded on invoice and are available on request. EasiPoint Marketing Limited endeavours to ensure that the above data and any further advice is correct, however it cannot accept any direct or indirect liability for the use of its products as such usage is beyond its control. Users should ensure that the product is suitable for their proposed application.

## BENEFITS

- ✓ Ensures strong bond to a wide range of substrates
- ✓ Complements EasiPoint paving range
- ✓ Can be used on damp surfaces
- ✓ Allows same-day trafficking

### Description

EasiPoint Slabfix is a hand-applied polyester mortar used for the bedding and fixing of paving where same day trafficking and/or exceptional bond is required.

### Material Classification

EasiPoint Slabfix is a polyester resin based bedding material supplied as a two-part pack ready for site mixing.

### Quality Assurance

EasiPoint Slabfix is manufactured under a quality system conforming to BS EN ISO 9001:2000.

### Compressive Strengths (all at 20°C):

2 Hours	6 Hours	8 Hours	24 Hours
25N/mm <sup>2</sup>	70N/mm <sup>2</sup>	76N/mm <sup>2</sup>	80N/mm <sup>2</sup>

### Set Times

Temperature (°C)	25	15	5	0
Set Times (mins)	20	40	80	160

### Approximate values depending on size of mix

Flexural Strength	25N/mm <sup>2</sup>
Tensile Strength	12N/mm <sup>2</sup>
Density	1900kg/m <sup>3</sup>
Youngs Modulus	15kN/mm <sup>2</sup>
Shrinkage	Less than 1% linear